



FO-xxM050

Clear PU Top coat for Parquet

Main features:

<ul style="list-style-type: none"> May be applied by spray, brush and roller coater Suitable for parquet 	<ul style="list-style-type: none"> Excellent abrasion resistance Excellent mat uniformity
--	---

Versions:

FO-20M050	20±5 Gloss	FO-40M050	40±5 Gloss	FO-70M050	70±5 Gloss
-----------	------------	-----------	------------	-----------	------------

Recommended use:	• Wooden flooring	• Stairs	• Flat parts
Application method:	Spray gun, brush and roller coater		
Product Preparation:	by weight:		by volume :
	hardener	FO-xxM050 100 FC---M050 100	same ratio as by weight

Chemical-physical features

Solid content (%)	31 ± 3
Specific gravity (g/cm ³)	0.980± 0.040
Viscosity DIN 4 (s) at 20°C	14 ± 1
Pot life (h)	6

Application features

Recommended quantity	max: 150 g/m ²
----------------------	---------------------------

General remarks on the application system

Drying at 20°C and R.H. between 45 and 65%: 100 g/m²	Forced drying: 100 g/m²	
	Temperature	Time
Dust free	Not recommended	
Touch free		
Stackable		
	Flash Off	
	Forced air	
	Cooling	

Substrate preparation: Substrate should be coated with FL---M050 and after drying it should be sanded. You can then proceed applying FO-xxM050

General remarks

Product may be applied by brush, roller coater or spray. We recommend the use of AF---M043, levelling agent, for spray applications to obtain the surfacing of the matt effect and a great final result. In case of spray application, you may use hardener FC---M042 80% ratio or FC---M080 at 80% ratio in order to obtain a quicker drying. Product has unlimited shelf life. However, after prolonged storage, some settlement may occur. It is therefore advisable to homogenize the product well before its use.